




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification³ : C07C 118/00, C08G 63/38 C08G 63/06, 63/00, 65/40 C08G 79/00	A1	(11) International Publication Number: WO 85/ 02184 (43) International Publication Date: 23 May 1985 (23.05.85)
(21) International Application Number: PCT/US84/01630 (22) International Filing Date: 10 October 1984 (10.10.84) (31) Priority Application Number: 552,234 (32) Priority Date: 16 November 1983 (16.11.83) (33) Priority Country: US (71) Applicant: THE DOW CHEMICAL COMPANY [US/ US]; 2030 Dow Center, Abbott Road, Midland, MI 48640 (US). (72) Inventors: WOO, Edmund, P. ; 300 Mayfield Lane, Midland, MI 48640 (US). MURRAY, Daniel, J. ; 3082 Shattuck Arms, Apt. #10, Saginaw, MI 48603 (US). (74) Agent: RUSSELL, H., David; The Dow Chemical Company, P.O. Box 1967, Midland, MI 48641-1967 (US).		(81) Designated States: AU, BR, JP. Published <i>With international search report.</i> <i>With amended claims.</i>

(54) Title: POLYAROMATIC CYANATES, A PROCESS FOR PREPARING THE POLYAROMATIC CYANATES, AND POLYTRIAZINES PREPARED FROM THE POLYAROMATIC CYANATES

**(57) Abstract**

A polyaromatic cyanate characterized by having formula (I), wherein: Ar is an aromatic radical; B is a C₇₋₂₀ polycyclic aliphatic radical; D is independently in each occurrence any nonactive hydrogen-containing substituent; q, r and s are independently in each occurrence the integers 0, 1, 2, or 3; with the proviso that the sum of q, r and s is greater than or equal to 2; t is independently in each occurrence an integer of between 0 and 4 inclusive; and x is a number between 0 and 5 inclusive. Another aspect of this invention is a process for the preparation of the polyaromatic cyanates. This process is characterized by first preparing cyanogen chloride in situ in a chlorinated hydrocarbon solution. The aqueous layer containing the alkali metal chloride by-product is separated from the chlorinated hydrocarbon layer. Then the polyaromatic cyanate is prepared by contacting a bridge hydroxy-substituted polyaromatic compound with the cyanogen chloride solution. Another aspect of this invention is a polytriazine characterized as being the reaction product of (a) between 1 and 100 mole percent of the polyaromatic cyanate ester of this invention and (b) between 0 and 99 mole percent of one or more cyanate-containing compounds known in the art as useful for the preparation of polytriazines.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GA	Gabon	MR	Mauritania
AU	Australia	GB	United Kingdom	MW	Malawi
BB	Barbados	HU	Hungary	NL	Netherlands
BE	Belgium	IT	Italy	NO	Norway
BG	Bulgaria	JP	Japan	RO	Romania
BR	Brazil	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	LI	Liechtenstein	SN	Senegal
CH	Switzerland	LK	Sri Lanka	SU	Soviet Union
CM	Cameroon	LU	Luxembourg	TD	Chad
DE	Germany, Federal Republic of	MC	Monaco	TG	Togo
DK	Denmark	MG	Madagascar	US	United States of America
FI	Finland	ML	Mali		
FR	France				

-1-

POLYAROMATIC CYANATES, A PROCESS FOR
PREPARING THE POLYAROMATIC CYANATES, AND POLYTRIAZINES
PREPARED FROM THE POLYAROMATIC CYANATES

The invention relates to polyaromatic cyanates, a process for preparing the polyaromatic cyanates and to polytriazines prepared from the polyaromatic cyanates.

It is known from German Patent Specification
5 No. 1,190,184 that high molecular weight polytriazines
can be obtained by polymerizing difunctional or poly-
functional aromatic cyanates at elevated temperature,
optionally in the presence of polymerization promoters.
The polymers are characterized for example by their
10 remarkable stability at elevated temperatures and they
are duroplastic in character after tempering for a suf-
ficiently long period. The resistance of the polytri-
azines to acids and various solvents may also be empha-
sized.

15 In addition, it was found by V. V. Korchak
et al. (cf. Vysokomolekulyarnye Soedineniya 1974,
number 1, pages 15 to 21) that the thermal and thermo-oxi-
dative destruction of polytriazines based on aromatic
cyanates is greatly influenced by moisture.




-2-

Finally, it is known from German Patent 1,720,740 that polyfunctional aromatic cyanates can be combined with powder-form and/or fibrous fillers or reinforcing materials and subjected either to a preliminary or subsequent heat treatment at about 50°C to 150°C, the resulting molding composition molded and hardened at temperatures in the range from about 150°C to 250°C. In many cases the resulting moldings also show inadequate thermal stability after storage in a moist, tropical atmosphere.

Polyaromatic cyanates which prepare polytriazines which are hydrolytically stable are needed. Polyaromatic cyanates which are useful in preparing polyaromatic triazines which are thermally stable are further needed.

The invention is directed to a polyaromatic cyanate characterized by having the formula



wherein:

- Ar is an aromatic radical;
- B is a C₇₋₂₀ polycyclic aliphatic radical;
- D is any nonactive hydrogen-containing substituent;
- q, r and s are independently in each occurrence the integers 0, 1, 2, or 3; with the proviso



-3-

that the sum of q, r and s is greater than or equal to 2;

t is independently in each occurrence an integer of between 0 and 4; and

5 x is a number between 0 and 5.

Another aspect of this invention is a process for the preparation of the polyaromatic cyanates. This process is characterized by first preparing cyanogen chloride in situ by contacting a solution of chlorine
10 in a chlorinated hydrocarbon with an aqueous solution of alkali metal cyanide. Then the aqueous layer containing the alkali metal chloride by-product is separated from the chlorinated hydrocarbon layer containing the cyanogen chloride. Then a solution of a
15 polycyclic bridged hydroxy-substituted polyaromatic phenol in a suitable solvent is contacted with the cyanogen chloride solution in the presence of a tertiary amine to prepare the polyaromatic cyanates of this invention.

20 Another aspect of this invention is a polytriazine characterized as being the reaction product of (a) between 1 and 100 mole percent of the polyaromatic cyanate ester of this invention and (b) between 0 and 99 mole percent of one or more cyanate-containing
25 compounds known in the art as useful for the preparation of polytriazines.

The novel polyaromatic cyanates of this invention prepare polytriazines which are surprisingly more stable to hydrolysis than prior art polytriazines.

30 The polytriazines of this invention can be used as cure-in-place resins or fabricated in the form






-4-


of shaped articles, where thermal stability, chemical inertness and solvent resistance are desirable or required.

Aromatic radical, Ar, refers herein to any radical containing an aromatic group. Examples of aromatic radicals include benzene, naphthalene, phenanthracene, anthracene, or biaromatic radicals, or two or more aromatic radicals bridged by alkylene moieties. Ar is preferably a benzene, naphthalene, biphenyl, benaphthyl, or a diphenylalkylene radical. Ar is more preferably a benzene radical.


Polycyclic aliphatic radical refers herein to any aliphatic radical which contains two or more cyclic rings. The polycyclic aliphatic radicals may contain one or more double or triple bonds. Preferred polycyclic aliphatic radicals correspond to the formulas



-5-



X,



XI,




XII and



XIII,

wherein:



and D^1 is C_{1-5} alkyl.

B is more preferably a radical which corresponds to one of the formulas II, III, IV, V, VI, VII, VIII or XIII with radicals corresponding to formulas II, III, IV, V or XIII being even more preferred, and radicals corresponding to formula II being most preferred.

D is any substituent which can be substituted on an organic hydrocarbon radical, with the exception that the substituent cannot contain an active hydrogen atom. Substituents within the scope of this invention are well-known to those skilled in the art. Active hydrogen atom means herein a hydrogen atom which is bonded to an oxygen, sulfur or nitrogen atom. Examples of substituents within the scope of D include alkyl, alkenyl, alkynyl, aryl, alkaryl, aralkyl, halo, alkoxy,




-6-

nitro, carboxylate, sulfone, sulfide or carbonate moieties. Preferred substituents are C₁₋₁₀ alkyl, C₁₋₁₀ alkenyl, nitro, and halo moieties, with C₁₋₃ alkyl, C₁₋₃ alkynyl, bromo and chloro moieties being most preferred.

Preferably, q, r and s are independently 1 or 2, and are most preferably 1. Preferably, t is independently an integer of 0, 1 or 2, more preferably 0 or 1, and most preferably 0. Preferably, x is between 0 and 2 inclusive, and more preferably between 0 and 1 inclusive.

The polyaromatic cyanates of this invention usually exist as a mixture of many isomers. Further, these polyaromatic cyanates usually are found as a mixture of compounds in which x is between 0 and 5. Usually the number given for x in a particular mixture is an average number.

In one preferred embodiment the polyaromatic cyanates correspond to the formula



wherein x is a real number of between 0 and 5, inclusive.

The polyaromatic cyanate esters of this invention are generally prepared by contacting a suitable polyaromatic phenol with cyanogen chloride, in the



-7-

presence of a tertiary amine. It is preferable to prepare the cyanogen chloride in situ by contacting a solution of chlorine in a chlorinated hydrocarbon solvent with an aqueous solution of an alkali metal cyanide. The reaction mixture separates into an organic layer of the chlorinated hydrocarbon containing the cyanogen chloride and an aqueous layer containing the alkali metal chloride salt. Generally, the alkali metal cyanide and chlorine are reacted in a molar ratio of between 1.0:1.0 and 1.0:1.15, preferably between 1.0:1.0 and 1.0:1.05; and most preferably 1.0:1.0. An excess of either may result in undesirable consequences, that is, excess chlorine may later react with the phenol, and excess alkali metal cyanide may result in a lower product purity. This contacting is done at a temperature of 0°C or below, preferably less than -15°C. Above 0°C the cyanogen chloride will trimerize. Preferable solvents for the chlorine are the aliphatic chlorinated hydrocarbons, such as, for example, methyl chloride, chloroform, and 1,1,1-trichloroethane. The preferred alkali metal cyanide is sodium cyanide.


The aqueous layer and organic layer are then separated. The separation of the organic layer from the aqueous layer is advantageous as the presence of the aqueous layer in further processing adversely affects the purity of the polyaromatic cyanates eventually prepared.

The organic layer containing the cyanogen chloride is then contacted with a polycyclic bridged hydroxy-substituted polyaromatic compound dissolved in a suitable solvent in the presence of a tertiary amine.




-8-

Polycyclic bridged hydroxy-substituted polyaromatic compounds useful in this process correspond to the formula



wherein Ar, B, D, q, r, s, t and x are as defined hereinbefore.

In one preferred embodiment the polycyclic bridged hydroxy-substituted polyaromatic compounds correspond to the formula



wherein x is as defined hereinbefore. The polycyclic bridged hydroxy-substituted polyaromatic compounds used usually exist as a mixture of isomers. Further, the polycyclic bridged hydroxy-substituted polyaromatic compounds are found as a mixture of compounds in which x is between 0 and 5. Usually the number given for x is an average number. The solvents used for the polycyclic bridged hydroxy-substituted polyaromatic compounds are secondary alcohols, tertiary alcohols, or chlorinated hydrocarbons. Preferred solvents are secondary alcohols or aliphatic chlorinated hydrocarbons, with isopropyl alcohol and methylene chloride most preferred.



-9-

The process is preferably done at a temperature of 0°C or below, more preferably -15°C or below.

For complete conversion of the hydroxy moieties on the aromatic radicals to cyanate moieties, at least 1 mole of cyanogen chloride for each hydroxy equivalent is needed. It is preferable to use an excess of 10 mole percent of cyanogen chloride for each hydroxy equivalent to insure complete conversion.

The tertiary amine acts as a hydrochloride acceptor, and as a result a tertiary amine hydrochloride salt is a by-product of the process. Generally, at least one mole of tertiary amine for each hydroxy equivalent is used. Hydroxy equivalent refers herein to the average molecular weight of the polycyclic bridged hydroxy-substituted polyaromatic compound divided by the average number of hydroxy moieties per molecule.

The polyaromatic cyanates can be recovered from the reaction solution in the following manner.

The reaction mixture is first contacted with a dilute aqueous solution of base, such as a bicarbonate, to remove the excess cyanogen chloride. Then the reaction mixture is contacted with water to remove the tertiary amine hydrogen chloride salt. Thereafter, the reaction solution is contacted with a dilute aqueous acid solution to neutralize any base present. A 1-20 weight percent solution of hydrochloride, phosphoric or sulfuric acid can be used, preferably a 5-10 weight percent solution. The reaction solution is then contacted with water to remove any impurities which may be present. The reaction solution is dried over a dessicant to remove the water, and the solvent is stripped off.



-10-

The polyaromatic cyanate recovered is of surprisingly high purity and can be used directly to prepare polytriazines.

5 The polycyclic bridged hydroxy-substituted polyaromatic compounds useful in this invention can be prepared by reacting an aromatic compound, containing at least one aromatic hydroxy moiety and one position on the aromatic ring which can be alkylated, with an unsaturated polycyclic aliphatic compound under conditions
10 such that a polycyclic bridged hydroxy-substituted polyaromatic compound useful in this invention is prepared.

Suitable substituted aromatic hydroxy compounds which can be employed herein include any such
15 compounds which contain one or two aromatic rings, at least one phenolic hydroxyl group and at least one ortho or para ring position with respect to a hydroxyl group available for alkylation.

Particularly suitable hydroxy-substituted
20 aromatic compounds which can be employed herein include, for example, phenol, chlorophenol, bromophenol, methylphenol, hydroquinone, catechol, resorcinol, guaiacol, pyrogallol, phloroglucinol, isopropylphenol, ethylphenol, propylphenol, t-butylphenol, isobutylphenol, octylphenol,
25 nonylphenol, cumylphenol, p-phenylphenol, o-phenylphenol, m-phenylphenol, bisphenol A, dihydroxydiphenyl sulfone, or mixtures thereof.

The hydroxy-substituted polyaromatic compound is contacted with the unsaturated polycyclic aliphatic
30 compound optionally in the presence of a solvent.



-11-

Preferred solvents include chlorinated hydrocarbons, aliphatic hydrocarbons; aromatic hydrocarbons and nitro-substituted hydrocarbons. In general the hydroxy-

5 the unsaturated polycyclic aliphatic compound is contacted with a mole ratio of between 20.0:1.0 and 1.0:1.0, preferably between 10.0:1.0 and 1.5:1.0.

These reactants are preferably contacted in the presence of a catalyst.

10 Acid catalysts which can be employed herein include, for example, Lewis acids, alkyl, aryl and aralkyl sulfonic acids, and disulfonic acids of diphenyl-oxide and alkylated diphenyloxide, sulfuric acid, or mixtures thereof. Preferable catalysts are such Lewis

15 acids as BF_3 gas, organic complexes of boron trifluoride such as those complexes formed with phenol, cresol, ethanol, or acetic acid. Also Lewis acids include, for example, aluminum chloride, zinc chloride, or stannic chloride. Also catalysts include, for example, activated

20 clays, silica, or silica-alumina complexes.

In preparing the compounds which contain an average of more than one phenolic hydroxyl group and more than one aromatic ring per molecule, the reaction between the phenolic hydroxyl-containing compounds and

25 the unsaturated hydrocarbons can be conducted at temperatures of from 33°C to 270°C, preferably from 33°C to 210°C.


The polyaromatic cyanates of this invention are useful in preparing polytriazines. The polytriazines of this invention comprise the reaction product

30



-12-

of (a) between 1 and 100 percent by weight of the polyaromatic cyanate of this invention, and (b) between 0 and 99 percent by weight of a cyanate which is useful for preparing triazines, such cyanates being well-known to those skilled in the art. The prior art cyanates useful in this invention include those corresponding to the formula $\text{Ar}(\text{OCN})_n$ wherein Ar is an aromatic radical, and n is an integer of from 1 to 5. Preferable cyanates include those corresponding to the formula




wherein

each R is the same or different and represents hydrogen, halogen, straight and branched $\text{C}_1\text{-C}_{20}$ alkyl, phenyl, alkoxy radicals having from 1 to 4 carbon atoms, alkoxy carbonyl radicals having from 1 to 4 carbon atoms in the alkyl group; or two adjacent radicals R on the same nucleus may together form a carbocyclic 5- or 6-membered ring, two adjacent radicals R may, together with a hetero atom (O, S, N), form a 5- or 6-membered heterocyclic ring,


R' has the same meaning as R or represents the group



-13-



5 A represents a direct bond, a C_1 - C_{20} alkylene group optionally substituted by C_1 - C_4 alkyl or phenyl, a cycloaliphatic or aromatic 5- or 6-membered ring optionally interrupted by oxygen, a sulfonyl group ($-SO_2-$), a carbonyl dioxido
10 group,



or a carbonyl group;

15 a represents a number of from 1 to 5 when $e \geq 1$, and a number of from 2 to 5 when $e=0$;
 b represents 5-a when $e \geq 1$ and 6-(a+d) when $e=0$;
 c represents 5-d;
20 d represents a number of from 0 to 5, and
 e represents 0, 1, 2 or 3,

with a proviso that the sum of a and d is always a number from 2 to 5.

25 The following compounds are specifically mentioned as examples of conventional cyanates within one or more of the formulas noted above: 1,3- and 1,4-dicyanatobenzene, 2-tert-butyl-1,4-dicyanatobenzene,



-14-

2,4-dimethyl-1,3-dicyanatobenzene, 2,5-di-tert-butyl-
-1,4-dicyanatobenzene, tetramethyl-1,4-dicyanatobenzene,
2,4,6-trimethyl-1,3-dicyanatobenzene, 4-chloro-1,3-dicya-
natobenzene, 1,3-, 1,4-, 1,5-, 1,6-, 1,7-, 1,8-, 2,6- or
5 2,7-dicyanatonaphthalene, 1,3,5-tricyanatobenzene; 4,4'-di-
cyanatodiphenyl, 2,2'-dicyanatodiphenyl, 3,3',5,5'-tetra-
methyl-4,4'-dicyanatodiphenyl, 3,3',5,5'-tetrachloro-4,4'-
-dicyanatodiphenyl, 3,3',5,5'-tetrachloro-2,2'-dicyanato-
diphenyl, 2,2',6,6'-tetrachloro-4,4'-dicyanatodiphenyl,
10 4,4'-bis-[(3-cyanato)-phenoxy]-diphenyl, 4,4'-bis-[(4-cy-
anato)-phenoxy]-diphenyl; 2,2'-dicyanato-1,1'-binaphthyl;
4,4'-dicyanatodiphenyl ether, 3,3',5,5'-tetramethyl-4,4'-
-dicyanatodiphenyl ether, 3,3',5,5'-tetrachloro-4,4'-di-
cyanatodiphenyl ether, 4,4'-bis-[p-cyanatophenoxy]-diphe-
15 nyl ether, 4,4'-bis-[p-cyanatophenylisopropyl]-diphenyl
ether, 4,4'-bis-[p-cyanatophenoxy]-benzene, 4,4'-bis-[m-
-cyanatophenoxy]-diphenyl ether, 4,4'-bis-[4-(4-cyanato-
phenoxy)-phenyl sulfone]-diphenyl ether; 4,4'-dicyanato-
diphenyl sulfone, 3,3',5,5'-tetramethyl-4,4'-dicyanato-
20 diphenyl sulfone, 3,3',5,5'-tetrachloro-4,4'-dicyanato-
diphenyl sulfone, 4,4'-bis-[p-cyanatophenylisopropyl]-
-diphenyl sulfone, 4,4'-bis-[(4-cyanato)-phenoxy]-diphe-
nyl sulfone, 4,4'-bis-[(3-cyanato)-phenoxy]-diphenyl sul-
fone, 4,4'-bis-[4-(4-cyanatophenylisopropyl)-phenoxy]-
25 -diphenyl sulfone, 4,4'-bis-[4-cyanatophenyl sulfone)-
-phenoxy]-diphenyl sulfone, 4,4'-bis-[4-(4-cyanato)-di-
phenoxy]-diphenyl sulfone, 4,4'-dicyanatodiphenyl meth-
ane, 4,4'-bis-[p-cyanatophenyl]-diphenyl methane, 2,2-
-bis-(p-cyanatophenyl)-propane, 2,2-bis-(3,5-dimethyl-
30 -4-cyanatophenyl)-propane, 2,2-bis-(3,5-dichloro-4-cya-
natophenyl)-propane, 1,1-bis-[p-cyanatophenyl]-cyclohex-
ane, bis-[2-cyanato-1-naphthyl]-methane, 1,2-bis-[p-cya-
natophenyl]-1,1,2,2-tetramethyl ethane, 4,4'-dicyanato-
benzophenone, 4,4'-bis-(4-cyanato)-phenoxybenzophenone,



-15-

1,4-bis-[p-cyanatophenylisopropyl]-benzene, 2,2',5,5'-
-tetracyanatodiphenyl sulfone; polycyanic acid esters of
novolaks (reaction products of phenol or alkyl- or
halogen-substituted phenols with formaldehyde in acid
5 solution) having from 3 to 5 OCN groups and the like.
Preferred conventional cyanate containing compounds
include 2,2-bis(p-cyanatophenyl)-propane and 2,3-bis-
(3,5-dibromo-4-cyanatophenyl)-propane.

The polytriazines of this invention prefer-
10 ably comprise the reaction product of (a) between 25
and 100 percent by weight of the polyaromatic cyanates
of this invention, and (b) between 0 and 75 percent by
weight of a cyanate which is useful in preparing polytri-
azines. More preferably, the polytriazines of this
15 invention comprise the reaction product (a) between 50
and 100 percent by weight of a polyaromatic cyanate of
this invention, and (b) between 0 and 50 percent by
weight of a cyanate useful in preparing polytriazines.
The prior art cyanates may comprise mono-, di- and
20 polycyanates.

The polytriazines of this invention may com-
prise up to 30 percent of monocyanate compounds, for
example, $\text{Ar}(\text{OCN})_n$ wherein $n=1$. The use of monocyanates
give the polytriazines modified properties, for example,
25 solubility, glass transition temperature, moisture
resistance and impact resistance.

The formation of polytriazines arise from the
cyclotrimerization of aryl cyanates to prepare 1,3,5-tri-
aryloxytriazines. The use of the difunctional and
30 polyfunctional polyaromatic cyanates of this invention



-16-

in the cyclotrimerization process results in the preparation of a three dimensional network polymer which is hard, infusible and insoluble.

The term polytriazines as used in this invention refer to both fully cured polytriazine polymers, and partially cured polytriazine prepolymers. Fully cured polytriazines are essentially free of cyanate functionalities. The prepolymers are cyanate group-containing polytriazines of liquid, wax-like or solid consistency and are soluble in organic solvents. These prepolymers are highly stable in storage. These prepolymers may be later converted to high molecular weight polytriazines when exposed to polymerization conditions. Prepolymers are prepared to permit easy handling of a resin prior to final use. Further, these prepolymers are useful in the production of coatings on such substrates as metals, ceramics, glass and earthenware, and as impregnating lacquers or laminating resins.

In the preparation of the polytriazines, aromatic polycyanates are contacted in the presence of a catalyst at a temperature of between 20°C and 200°C, optionally in the presence of a solvent. Preferable temperatures are between 80°C and 180°C. The prepolymers are prepared by the same process, except either a lower temperature or a lower amount of catalyst is used, so that the aromatic polycyanates do not completely polymerize.

The rate of polymerization is dependent upon the temperature and the catalyst amount. As either, or both, increase, the rate of polymerization increases. At higher temperatures, a lower amount of catalyst is



-17-

necessary for the desired amount of polymerization than is necessary at lower temperatures.

Useful catalysts include acids, bases, salts, nitrogen and phosphorus compounds, for example, Lewis acids such as AlCl_3 , BF_3 , FeCl_3 , TiCl_4 , ZnCl_2 , SnCl_4 ; proton acids such as HCl , H_3PO_4 ; aromatic hydroxy compounds such as phenol, p-nitrophenol, pyrocatechol, dihydroxy naphthalene, sodium hydroxide, sodium methy-
5 late, sodium phenolate, trimethylamine, triethylamine, tributylamine, diazobicyclo-(2,2,2)-octane, quinoline, iso-quinoline, tetrahydroisoquinoline, tetraethyl ammonium chloride, pyridine-N-oxide, tributylphosphine, phospho-
10 line- Δ^3 -1-oxa-1-phenyl, zinc octoate, tin octoate, zinc naphthenate, cobalt salts of C_{6-20} carboxylic acids and
15 mixtures thereof. Preferable catalysts are the cobalt salts of C_{6-20} carboxylic acids, with cobalt naphthenate and cobalt octoate being most preferred.

Generally, any amount of catalyst which catalyzes the preparation of polytriazines is suitable.
20 Preferably, between 0.001 and 10 percent by weight of the cyanates of catalyst is used.

Solvents useful in this invention can be any compound which dissolves the aromatic polycyanates and does not interfere with the reaction. Suitable solvents
25 include aromatic hydrocarbons, alcohols and ketones.

The polyfunctional aromatic polycyanates may be combined with the powder-form or fibrous fillers or reinforcing materials either before or after heat treatment of the aromatic polycyanates and by basically
30 any method. For example it is possible to impregnate



-18-

powder-form or fibrous fillers or reinforcing materials such as quartz sand or glass cloths, with the aromatic cyanates, optionally in solution. Examples of the solvents which may be used for this purpose and which, generally, have to be removed again afterwards, are inert solvents such as methylene chloride, acetone, methylethyl ketone, xylene, ethyl acetate benzene, toluene, tetrahydrofuran, chlorobenzene, dibutyl ether, dimethyl formamide and tetramethylene sulfone.

Suitable fillers and reinforcing materials are, generally, in any powder form and/or fibrous products, for example, of the type commonly used in the production of moldings based on unsaturated polyester resins or epoxide resins. Examples of products such as these are, primarily, granular fillers such as quartz powder, ground shale, asbestos powder, powdered corundum, chalk, iron powder, aluminum powder, sand, or gravel, also inorganic or organic fibers, more especially glass fibers in the usual textile forms of fibers, filaments, rovings, yarns, nonwovens, mats or cloths. In this connection, amino silane-based finishes have proven to be particularly effective. It is also possible to use corresponding textile structures of organic, preferably synthetic fibers (polyamides, polyesters) or on the basis of quartz, carbon, metals, etc., as well as monocrystals (whiskers).

The end products combined with fillers or reinforcing materials may be used in particular in vessel and pipe construction by the winding technique, in electrical engineering, in mold construction and tool making and also in the construction of heavily stressed components, in the lightweight construction of vehicles in aeronautical and astronautical engineering.




-19-


The following examples are included for illustrative purposes only, and are not intended to limit the scope of the invention or claims.

Example 1


- 5 Polytriazine castings of each of the following cyanate-containing compounds are prepared.



10



15 and



20 wherein formula I is an example of this invention and formulas II and III are not.

The polytriazine castings of the aromatic cyanates of formulas I and II are prepared by heating



-20-

about 6 g of the respective cyanate along with about 200 parts per million of cobalt naphthenate at 150°C for 1 hour and 20 minutes and then at 200°C for 3 hours.

- 5 The castings of formula III are prepared by heating about 6 g of formula III along with 200 parts per million of cobalt naphthenate at 180°C for 2 hours and 250°C for 90 minutes.

- 10 All of the castings are monitored by differential scanning calorimetry to insure the castings have no uncured cyanate functionalities.

- 15 A casting of each of the polytriazines is exposed to the following test conditions. In Test 1, the castings are boiled in water for 96 hours. In Test 2, the castings are immersed in 20 weight percent hydrochloric acid for 2.5 hours at room temperature and then at reflux for 4.5 hours. In Test 3, the castings are immersed in 40 weight percent sodium hydroxide at room temperature for 2.5 hours, then at reflux for 4.5 hours.
- 20

Each casting is weighed before and after each test. Table I compiles the test results.

TABLE I

25 Test	Weight Change (%)		
	Cyanate I	Cyanate II	Cyanate III
1	+0.63	+ 1.08	+1.26
2	+0.26	- 4.35	+1.55
3	-1.69	-28.68	-5.78



-21-

The weight gains are due to the adsorption of water by the samples. The weight losses are due to the decomposition of the polymer due to hydrolysis. Generally, water is adsorbed by the polymer prior to hydrolysis.

5 The example demonstrates that the polytriazine prepared from the compound corresponding to formula I is significantly more resistant to hydrolysis than the polytriazines prepared from compounds corresponding to formula II or III. Visual inspection of the castings
10 after Test 2 shows that the casting prepared from the compound corresponding to formula I has no change in appearance, whereas the casting prepared from the compound corresponding to formula II has lost its transparency due to surface pitting. A visual inspection
15 after Test 3 of the casting prepared from the compound corresponding to formula I shows slight surface pitting, whereas a visual inspection of the castings prepared from the compound corresponding to formula II after Test 3 shows the casting to have numerous voids throughout
20 and that the casting readily crumbles under physical stress.


Example 2

 An 85 percent solution of polyaromatic cyanate I in methyl isobutyl ketone containing 0.016
25 weight percent of cobalt naphthenate are used to impregnate fiberglass cloth. Eight plies of the impregnated cloth are laid up and cured in a press at 175°C and 300 psi (2.07 MPa) for 1 hour to give a 0.062 inch (1.57 mm) thick laminate which has a glass transition temperature of 265°C. The laminate shows a 0.09
30 percent by weight absorption of water after boiling for an hour at 15 psi.



Example 3

A 50 percent solution of a polyaromatic cyanate corresponding to the formula



in methyl ethyl ketone containing 0.02 percent of cobalt octoate is used to impregnate fiberglass cloth, six plies of which are laid up and cured in a press at 175°C and 300 psi (2.07 MPa) for 1 hour. A laminate using the polyaromatic cyanate of formula II (not an example of the invention) is prepared in the same manner. Both laminates are subjected to humidity aging at 71°C for 1000 hours at 100 percent humidity. The laminate prepared from formula IV shows water absorption of 0.59 percent, while the laminate prepared from formula II absorbs 0.83 percent water (the experimental error is 0.01 percent). This example demonstrates that the polytriazines prepared from polyaromatic cyanates of this invention absorb significantly less water than polytriazines prepared from prior art cyanates.

Example 4

A fiberglass cloth laminate is prepared from a 50 percent solution of formula IV in methyl ethyl ketone without catalyst. The laminate is heated at 150°C for 15 minutes, and then inserted into a 215°C press at contact pressure. The temperature is raised



-23-

to 250°C over a period of 8 minutes and a pressure of 100 psi (0.689 MPa) is then applied. After 45 minutes, the laminate is removed and post-cured for 1 hour at 250°C and then for 1 hour at 275°C. The laminates are
5 of an E glass Style 7781, A 1100 Finish, 6-ply and 27 percent resin.

The laminate is divided into different portions and several tests are run. In the control, the flexural strength and flexural modulus are determined
10 at room temperatures (23°C) and 190°C. This testing is done in accordance with ASTM D-790. Other portions of the laminate are exposed to different conditions and thereafter the flexural strength and flexural modulus are tested.

15 In Test 4 the laminate is exposed to air at 200°C for 500 hours. In Test 5 the laminate is exposed to 100 percent humidity at 50°C for 570 hours. In Test 6 the laminate is immersed in CH_2Cl_2 for 7 days. In Test 7 the laminate is immersed in methanol for 7 days.
20 In Test 8 the laminate is immersed in toluene for 7 days. The percentage of the flexural strength and modulus of each laminate compared to the control at room temperature is calculated. The laminates are also weighed before and after each treatment and the percent
25 change relative to the standard is calculated. The results are compiled in Table II.

Table II demonstrates that glass laminates prepared using the polyaromatic cyanates of this invention are stable to heat, humidity and contact with com-
30 mon solvents such as methanol and toluene.




TABLE II

<u>Test</u>	<u>Weight Change</u>	<u>Flexural Strength</u>				<u>Flexural Modulus</u>			
		<u>room temperature</u>		<u>190°C</u>		<u>room temperature</u>		<u>190°C</u>	
		10 ³ psi (MPa)	% of Standard	10 ³ psi (MPa)	% of Standard	10 ³ psi (MPa)	% of Standard	10 ³ psi (MPa)	% of Standard
Standard	-	70.5 (486)	-	66.0 (455)	94	3.08 (21.2)	-	3.19 (22.0)	103
4	- 0.23	63.7 (439)	90	58.9 (406)	84	3.23 (22.3)	105	3.12 (21.5)	101
5	+ 0.4	72.5 (500)	103	56.6 (390)	80	3.49 (24.1)	113	2.79 (19.2)	91
6	+12.56	43.5 (300)	62	-	-	2.09 (14.4)	68	-	-
7	+ 0.69	57.1 (394)	80	-	-	3.24 (22.3)	105	-	-
8	+ 0.27	73.3 (505)	104	-	-	3.21 (22.1)	104	-	-

-24-



1. A polyaromatic cyanate characterized by having the formula



wherein:

Ar is an aromatic radical;

B is a C₇₋₂₀ polycyclic aliphatic radical;

D is independently in each occurrence any nonactive hydrogen-containing substituent;

q, r and s are independently in each occurrence the integers 0, 1, 2, or 3; with the proviso that the sum of q, r and s is greater than or equal to 2;

t is independently in each occurrence an integer of between 0 and 4 inclusive; and

x is a number between 0 and 5 inclusive.





2. The composition of Claim 1 characterized in that:



-26-

Ar is a benzene, naphthalene, phenanthracene, anthracene, or biaromatic radicals, or two or more aromatic radicals bridged by alkylene moieties;

B is



D is an alkyl, alkenyl, alkynyl, aryl, alkaryl, aralkyl, halo, alkoxy, nitro, carboxylate,




-27-

sulfone, sulfide, or carbonate moiety;

D¹ is C₁₋₅ alkyl;

Y is




q, r and s are independently 1 or 2;

t is independently 0, 1 or 2; and

x is a number between about 0 and 2 inclusive.

3. The composition of Claim 1 characterized by having the formula



wherein x is a real number of between 0 and 5, inclusive.

4. The composition of Claim 6 wherein x is a real number of between 0 and 2, inclusive.

5. The composition of Claim 6 wherein x is a real number of between 0 and 1, inclusive.

6. A process for the preparation of the polyaromatic cyanate of Claim 1 characterized by




-28-

(a) preparing in situ a cyanogen chloride by contacting a solution of chlorine in a chlorinated hydrocarbon with an aqueous solution of an alkali metal cyanide at a temperature of 0°C or below under conditions such that a cyanogen chloride is prepared;

(b) physically separating the chlorinated hydrocarbon in which the cyanogen chloride is dissolved from the aqueous layer in which an alkali metal chloride salt is dissolved; and

(c) contacting the cyanogen chloride dissolved in the chlorinated hydrocarbon with a polycyclic bridged hydroxy-substituted polyaromatic compound dissolved in a chlorinated hydrocarbon, a secondary alcohol or a tertiary alcohol, in the presence of a tertiary amine at a temperature of about 0°C or less under conditions such that a polyaromatic cyanate is prepared;

wherein the polycyclic bridged hydroxy-substituted polyaromatic compound corresponds to the formula



wherein:

Ar is an aromatic radical;

B is a C₇₋₂₀ polycyclic aliphatic radical;

D is independently in each occurrence any nonactive hydrogen-containing substituent;

q, r and s are independently in each occurrence the integers 0, 1, 2, or 3; with the proviso



-29-

that the sum of q, r and s is greater than or equal to 2;

t is independently in each occurrence an integer of between 0 and 4 inclusive; and

x is a number between 0 and 5 inclusive.


7. A polytriazine characterized as being the reaction product of

(a) between 1 and 100 mole percent of the polyaromatic cyanate of Claim 1.

and (b) between 0 and 99 mole percent of one or more cyanate-containing compounds,

8. The polytriazine of Claim 7 characterized in that the cyanate-containing compound corresponds to the formula $\text{Ar}(\text{OCN})_n$ wherein Ar is an aromatic radical and n is an integer of between 1 and 5, inclusive.

9. The polytriazine of Claim 7 characterized in that the cyanate-containing compound corresponds to the formula



wherein


each R is the same or different and represents hydrogen, halogen, straight and branched $\text{C}_1\text{-C}_{20}$ alkyl, phenyl, alkoxy radicals having from 1 to 4 carbon atoms, alkoxy carbonyl radicals having




-30-

from 1 to 4 carbon atoms in the alkyl group or; two adjacent radicals R on the same nucleus may together form a carbocyclic 5- or 6-membered ring, two adjacent radicals R may, together with a hetero atom (O, S, N), form a 5- or 6-membered heterocyclic ring,

R' has the same meaning as R or represents the group



A represents a direct bond, a C₁-C₂₀ alkyl-ene group optionally substituted by C₁-C₄ alkyl or phenyl, a cycloaliphatic or aromatic 5- or 6-membered ring optionally interrupted by oxygen, a sulfonyl group (-SO₂-), a carbonyl dioxide group,



or a carbonyl group;

a represents a number of from 1 to 5 when e ≥ 1, and a number of from 2 to 5 when e = 0;

b represents 5-a when e ≥ 1 and 6-(a+d) when e = 0;

c represents 5-d;

d represents a number of from 0 to 5, and

e represents 0, 1, 2 or 3,


with a proviso that the sum of a and d is always a number from 2 to 5.



-31-

ABSTRACT

This invention relates to a polyaromatic cyanate characterized by having the formula



wherein:

- Ar is an aromatic radical;
- B is a C₇₋₂₀ polycyclic aliphatic radical;
- D is independently in each occurrence any nonactive hydrogen-containing substituent;
- q, r and s are independently in each occurrence the integers 0, 1, 2, or 3; with the proviso that the sum of q, r and s is greater than or equal to 2;
- t is independently in each occurrence an integer of between 0 and 4 inclusive; and
- x is a number between 0 and 5 inclusive.



-32-

Another aspect of this invention is a process for the preparation of the polyaromatic cyanates. This process is characterized by first preparing cyanogen chloride in situ in a chlorinated hydrocarbon solution.

- 5 The aqueous layer containing the alkali metal chloride by-product is separated from the chlorinated hydrocarbon layer. Then the polyaromatic cyanate is prepared by contacting a bridged hydroxy-substituted polyaromatic compound with the cyanogen chloride solution.

- 10 Another aspect of this invention is a polytriazine characterized as being the reaction product of (a) between 1 and 100 mole percent of the polyaromatic cyanate ester of this invention and (b) between 0 and 99 mole percent of one or more cyanate-containing
15 compounds known in the art as useful for the preparation of polytriazines.




AMENDED CLAIMS

[received by the International Bureau on 24 January 1985 (24.01.85);
original claims 4 and 5 amended; remaining claims unchanged (1 page)]

sulfone, sulfide, or carbonate moiety;

D¹ is C₁₋₅ alkyl;

Y is




q, r and s are independently 1 or 2;

t is independently 0, 1 or 2; and

x is a number between about 0 and 2 inclusive.

3. The composition of Claim 1 characterized by having the formula



wherein x is a real number of between 0 and 5, inclusive.

4. The composition of Claim 3 wherein x is a real number of between 0 and 2, inclusive.

5. The composition of Claim 3 wherein x is a real number of between 0 and 1, inclusive.

6. A process for the preparation of the polyaromatic cyanate of Claim 1 characterized by



INTERNATIONAL SEARCH REPORT

International Application No

PCT/US84/01630

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ¹

According to International Patent Classification (IPC) or to both National Classification and IPC
IPC: C07C 118/00; C08G 63/38, 06, 00; 65/40; 79/00

II. FIELDS SEARCHED

Minimum Documentation Searched ⁴

Classification System

Classification Symbols

US 260/453AP, 453P; 549/23, 49, 58; 528/174, 205, 208
528/211, 271, 380, 422; 544/180

Documentation Searched other than Minimum Documentation
to the Extent that such Documents are Included in the Fields Searched ⁵

III. DOCUMENTS CONSIDERED TO BE RELEVANT ¹⁴

Category ¹ | Citation of Document, ¹⁵ with indication, where appropriate, of the relevant passages ¹⁷ | Relevant to Claim No. ¹⁸

A US, A, 3,231,595, published 25 January 1966
Brotherton

A US, A, 3,141,900, published 21 July 1964
Lynn

Y US, A, 4,195,132, published 25 March 1980
Lundermann

1-5, 7-9

Y GB, A, 1526035, published 27 September 1978
Lundermann

1-9

Y US, A, 4,046,796, published 06 September 1977
Lundermann

6

* Special categories of cited documents: ¹⁶

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

IV. CERTIFICATION

Date of the Actual Completion of the International Search ¹

17 December 1984

International Searching Authority ¹

ISA/US

Date of Mailing of this International Search Report ¹

24 DEC 1984

Signature of Authorized Officer ¹⁹

Alan Siegel

FURTHER INFORMATION CONTINUED FROM THE SECOND SHEET

V. ☐ OBSERVATIONS WHERE CERTAIN CLAIMS WERE FOUND UNSEARCHABLE ¹⁰

This international search report has not been established in respect of certain claims under Article 17(2) (a) for the following reasons:

1. ☐ Claim numbers because they relate to subject matter ¹² not required to be searched by this Authority, namely:

2. ☐ Claim numbers because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out ¹³, specifically:

VI. ☒ OBSERVATIONS WHERE UNITY OF INVENTION IS LACKING ¹⁴

This International Searching Authority found multiple inventions in this international application as follows:

I Claims 1-5 drawn to polyaromatic isocyanates

II Claim 6 drawn to a process for producing polyaromatic isocyanates

III Claims 7-9 drawn to polytriazine resins

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims of the international application.

2. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims of the international application for which fees were paid, specifically claims:

3. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claim numbers:

4. ☐ As all searchable claims could be searched without effort justifying an additional fee, the International Searching Authority did not invite payment of any additional fee.

Remark on Protest

☐ The additional search fees were accompanied by applicant's protest.

☐ No protest accompanied the payment of additional search fees.